

1306

WOOD

3/4" DEEP 2" CEDAR GRAPESTAKES

ASTM				
D256 D256				
D638 D695				
D095 D1525				
	Attachment to Formwork			
D256	Thermoform Formliners can be used in precast, tilt-up or cast			
D256	-in-place applications. Single-use HIP is most frequently used			
D638 D638	for tilt-up applications and can be installed using Tek drywall screws or pneumatic staplers, spacing should be approxi- mately 6" to 12" on center around the perimeter and 18" to			
D790	24" through the center Double Sided Tape "Formica Ton"			

for tilt-up applications and can be installed using Tek drywall screws or pneumatic staplers, spacing should be approximately 6" to 12" on center around the perimeter and 18" to 24" through the center. Double Sided Tape, "Formica Top" adhesive, Heavy Duct Tape or Silicone Caulk are all the common ways to attach formliners. Make sure all surfaces are clean, dry and free of dust and debris. Formliner PE & PPE liners are attached from the back with 3/8" bolts when optional T-nuts are installed.

Form Placement

It is important that forms for architectural concrete be aligned and in common planes. A "Stack up" of manufacturing tolerances can result in forms being in different planes, even when properly aligned. This creates a noticeable "step" in the finished surface, particularly with shallow Formliner patterns.

Rustication

Reveals or rustications are recommended at butted joints so it will allow the features of the liner to appear continuous. All butted joints should be taped and/or caulked to reduce grout leakage.

Form Release

Formliners should be sprayed with high end form release agent before each use and within the same day that concrete is placed. Apply with low flow, wide angle, flat spray nozzle and wipe with a cloth to insure a complete even coat to the entire formliner surface.

TECHNI	TECHNICAL DATA			
Wood 1306 HIPS High Impact Polystyrene Plastic				
Properties IZOD Impact, ftlbs./in.	Rating	ASTM		
@70°F	2.0	D256		
@0°F	1.3	D256		
Tensile Strength	3,700 psi	D638		
Heat Deflection	188	D695		
Vicat Softening	212	D1525		
Wt.lb./sq.ft.				
.070 mil	.449			
.090 mil	.577			
.110 mil	.705			
.130 mil .150 mil	.833 .966			
. 150 mil	.900			
	1306 ABS	•		
IZOD Impact, ftlbs./in.				
20D Impact, πibs./in. @73°	5.6	D256		
@0°	1.9	D256		
Tensile Strength, 73°F, psi	1.5	D250		
Yield	5,300	D638		
Modulus	330,000	D638		
Flexural Strength 73°F, psi	,			
Yield	9,300	D790		
Modulus	325,000	D790		
Heat Deflection				
@264 psi	199	D648		
@66 psi	211	D648		
Hardness (Rockwell R) 73°F	105	D785		
Falling Dart Impact, ftlb.				
@73°F	23			
@40°F	14	D700		
Specific Gravity	1.05	D792		
Wt. lb./sq.ft. .070 mil	.451			
.090 mil	.580			
.110 mil	.705			
.130 mil	.833			
.150 mil	.961			
	1306 PE			
Polyurethane Elastomer				
Shore A Hardness	45-50	D2240		
Tear Strength, PLI	55	D624		
Tensile Strength, psi	500	D638 (D412)		
Ultimate Elongation	240%	D638 (D412)		
Wood 1306 PPE Premium Polyurethane Elastomer				
Shore Hardness	60-65	D2240		
Tear Strength, PLI	120	D2240 D624		
Tensile Strength, psi	1150	D638 (D412)		
Ultimate Elongation	1200%	D638 (D412)		
~ • •		- ()		
Manufacturing Tolerances @7				
Length: +1" to 2", -0" (shipped long to allow field trimming Width: $\pm 1/4$ "				
Width: $\pm 1/4$ " Thickness @ addes $\pm 1/16$ " (av	oont formliners	(or 1" thicknooc)		
Thickness @ edges ± 1/16" (ex	cept ionnimers of	ver i unickness)		